



Product description

MASTERS 170 is a one-component, acid-curing, low modulus silicone sealant for sanitary and DIY applications.

Special features

- solvent free
- exempt from withdrawal
- weather resistant
- excellent UV resistance
- suitable for use in sanitary areas - mold resistant
- non-sag
- ready gunnability at low (+5°C) and high (+40°C) temperatures
- flexible at low (-40°C) and high temperatures (+180°C)
- rapid crosslinking: quickly becomes tack-free
- excellent tooling properties for professional use
- excellent adhesion on glass, aluminium and ceramic
- good adhesion on plastics in general and a great part of paints
- does not hurt fishes

Application

- suitable for the construction of aquaria
- to seal joints exposed to high mechanical stress
- to seal joints which need to act quickly
- to stick and seal two or more glass elements
- it can be used in do-it-yourself aquarium industry

Restrictions on use

MASTERS 170 must not be used for insulating glass applications.

it is the responsibility of the user to test the compatibility of the sealant with the adjoining materials. Incompatible substances like coating materials (paints, varnishes and glazes) or organic plasticizer containing rubbers (EPDM, butyl and neoprene) can lead to discoloration or other impairments like loss of adhesion of the sealant. Materials in direct contact with the applied sealant like cleaning agents and materials in indirect contact like gaseous emissions can damage the sealant in its function or change its appearance. Because of the multitude of these materials, Mastici Vottero cannot make a general statement to the compatibility of materials with the sealant. In case of doubt the user shall conduct appropriate preliminary tests.

MASTERS 170 is not recommended for use on natural stones, such as marble, granite, quartzite, as it can cause staining.

MASTERS 170 should not be used on substrates such as concrete, fibrous

cement, and mortar, as the product releases acetic acid during.

MASTERS 170 should not be used in contact with metals such as lead, copper, brass or zinc due to corrosion.

MASTERS 170 is not suitable for food grade applications where the joints are likely to come in contact with food.

MASTERS 170 is not suitable for use as a mirror adhesive.

The time until complete curing may be extended at lower temperature, lower humidity, increasing film thickness or by low volume of air exchange.

The use of tooling agents should be avoided if possible. Otherwise, water or a diluted solution of a little neutral soap or alcohol in water should be sparingly applied.

Adhesion

MASTERS 170 exhibits excellent primerless adhesion to most material used for sanitary application, e.g. glass, tiles, ceramics, enamel, glazed tiles and clinker; varnished or painted wood; and some plastics.

Users must carry out their own tests due to the great variety of substances. The adhesion can be improved in many cases by pretreatment of the substrates with a primer.

If adhesion difficulties arise please contact our technical service.

Package

cartridge 310 ml, box 12/24 pc

drums 21 / 210 kg

Colours



Processing

The substrate areas that will be in contact with the sealant must be clean, dry and free of all loose material such as dust, dirt, rust, oil and other contaminants. Non-porous substrates should be cleaned with a solvent and a clean, lint-free, cotton cloth. Remove residual solvent before it evaporates with a fresh clean, dry cloth.

Storage

The 'Best use before end' date of each batch is shown on the product label.

Storage beyond the date specified on the label does not necessarily mean that the product is no longer usable. In this case however, the properties required for the intended use must be checked for quality assurance reasons. Stored in its original packaging, in a cold dry place (+5°C and +25°C), away

from direct sunlight, the product lasts 24 months.

Safety notes

During vulcanization acetic acid is released. These vapors should not be inhaled for long periods or in high concentration. Hence, good ventilation of the work place is necessary. Should uncured silicone rubber come into contact with eyes or mucous membranes, the affected area must be rinsed thoroughly with water as irritation will otherwise be caused. Cured silicone rubber, however, can be handled without any risk to health.

Comprehensive instructions are given in the corresponding Material Safety Data Sheets. They are available on request from MASTICI VOTTERO.

MASTERS 170 - Product data

General characteristics	Inspection method	unit	Value
Uncured paste			
Density at 23°C	ISO 1183-1 A	[g/cm ³]	1,03
Consistency	ISO 7390, profile U 20		non-sag
Extrusion rate - volume flow at 23°C		[ml/min]	250
Skin forming time at 23°C / 50% rh		[min]	15
Cured paste / Gomma vulcanizzata			
After 4 weeks storage at 23°C / 50% rh			
Tensile strength	ISO 8339	[N/mm ²]	0,80
Elongation at break	ISO 8339	[%]	200
Modulus at 100% elongation	ISO 8339	[N/mm ²]	0,55
Hardness Shore A	ISO 868		22
Tear Strength	ISO 34, method C	[N/mm]	6,1

These figures are only intended as a guide and should not be used in preparing specifications.

The data presented in this medium are in accordance with the present state of our knowledge but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this medium should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also being used. The information provided by us does not absolve the user from the obligation of investigating the possibility of infringement of third parties' rights and, if necessary, clarifying the position. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the product for a particular purpose.

The management system has been certified according to DIN EN ISO 9001 and DIN EN ISO 14001

For technical, quality, or product safety questions, please contact:
 MASTICI VOTTERO s.n.c.
 10040 La Cassa (TO) - via Torino 44
 info@masticivottero.com
 www.masticivottero.com