

# TECHNICAL DATA SHEET MASTERS POLYMER F-410

## Product description

MASTERS POLYMER F-410 is a one-component adhesive sealant based on hybrid polymer with silane termination. It cures according with air moisture reaction. Its good elasticity allows joints movement. Specifically suitable for bonding and sealing of plastic component.

#### **Specifications**

- single-component
- ready to use
- isocyanates and solvents free
- permanent elasticity
- excellent surface hardness
- odorless
- great chromatic stability
- can be over-coated
- adhesion without primer
- great extrusion
- adhesive properties unchanged over time
- excellent UV resistance

#### **Application areas**

It is suitable for gluing and sealing of a wide variety of surfaces such as:

- glass
- mirrors
- porcelain
- wood
- aluminium painted aluminium
- steel stainless steel
- iron
- bricks concrete
- plasterboard
- polyurethane panels
- polystyrene
- stone
- bus vans vehicles container
- PVC ABS PC PMMA Corian

#### Preparation and use

Conditions of use: use at a temperature between  $+5^{\circ}C$  and  $+50^{\circ}C$  - for a good performance of the product we suggest to use it at a temperature of 20°C.

It is advised to completely harden the product before painting.


*Surface requirements:* the surface should be dry, free of dust, oils, detergents and greases, once the surface has been cleaned, wait no more than 20 minutes for laying the product.

Tools for use: manual or pneumatic guns

Cleaning utensils: clean them with mineral turpentine.

*Spots and residues:* remove non-crosslinked parts with mineral turpentine, hardened parts can only be removed mechanically.

## **Application example**



### Package

cartridge 290 ml, box. 12/24 pc unipac 600 ml, box 20 pc drums 25 kg drums 250 kg

## Colours



## Storage

Stored in its original packaging, in a cold dry place (+5°C and +25°C), away from direct sunlight, the product lasts 24 months.

### Security measures

Avoid contact with mucous membranes and skin Use gloves to avoid irritation, especially in susceptible persons In case of contact with eyes, rinse with large amounts of water consult a doctor.

Avoid to release the packages to the environment

#### Notes

These informations and our technical specifications, correspond to our experience but these not establish our garantee in relationship with final results or responsability arising out of any legal report.

In view of the multiplicity of material handling and storage conditions, the conditions of production and use, all the above information and indications must be verified beforehand by the user in accordance with its specific conditions of use.

Curing time at 20°C / 45 % r.h.   [mm/24h]   2     Skin forming time at 23°C / 45 % r.h.   [min]   30     Cured paste     After 4 weeks storage at 23°C / 50% rh     Tensile strength   ISO 37   [N/mm <sup>2</sup> ]   2,10     Elongation at break   ISO 37   [%]   200     Modulus at 100% elongation   ISO 37   [N/mm <sup>2</sup> ]   1,80     Hardness Shore A   ISO 868   55     Volume loss   [%]   <-2	MASTERS POLYMER F-410 - Product data			
Density at 23°C     ISO 2811     [g/cm <sup>3</sup> ]     1,40       Consistency     non-say       Curing time at 20°C / 45 % r.h.     [mm/24h]     2       Skin forming time at 23°C / 45 % r.h.     [min]     30       Cured paste       After 4 weeks storage at 23°C / 50% rh       Tensile strength     ISO 37     [N/mm <sup>2</sup> ]     2,10       Elongation at break     ISO 37     [%]     200       Modulus at 100% elongation     ISO 37     [N/mm <sup>2</sup> ]     1,80       Hardness Shore A     ISO 868     55     55       Volume loss     [%]     <-2	General characteristics	Inspection method	unit	Value
Consistency     non-sag       Curing time at 20°C / 45 % r.h.     [mm/24h]     2       Skin forming time at 23°C / 45 % r.h.     [min]     30       Cured paste     After 4 weeks storage at 23°C / 50% rh     [min]     30       Cured paste     ISO 37     [N/mm²]     2,10       Elongation at break     ISO 37     [%]     200       Modulus at 100% elongation     ISO 37     [N/mm²]     1,80       Hardness Shore A     ISO 868     55     55       Volume loss     [%]     <-2	Uncured paste			
Curing time at 20°C / 45 % r.h.     [mm/24h]     2       Skin forming time at 23°C / 45 % r.h.     [min]     30       Cured paste     [min]     30       After 4 weeks storage at 23°C / 50% rh     [N/mm <sup>2</sup> ]     2,10       Tensile strength     ISO 37     [N/mm <sup>2</sup> ]     2,10       Elongation at break     ISO 37     [%]     200       Modulus at 100% elongation     ISO 37     [N/mm <sup>2</sup> ]     1,80       Hardness Shore A     ISO 868     55       Volume loss     [%]     <-2	Density at 23°C	ISO 2811	[g/cm <sup>3</sup> ]	1,40
Skin forming time at 23°C / 45 % r.h.     [min]     30       Cured paste     After 4 weeks storage at 23°C / 50% rh     [min]     30       Tensile strength     ISO 37     [N/mm²]     2,10       Elongation at break     ISO 37     [%]     200       Modulus at 100% elongation     ISO 37     [N/mm²]     1,80       Hardness Shore A     ISO 868     55       Volume loss     [%]     <-2	Consistency		N N	non-sag
Cured paste       After 4 weeks storage at 23°C / 50% rh       Tensile strength     ISO 37     [N/mm²]     2,10       Elongation at break     ISO 37     [%]     200       Modulus at 100% elongation     ISO 37     [%]     200       Hardness Shore A     ISO 868     55       Volume loss     [%]     <-2	Curing time at 20°C / 45 % r.h.		[mm/24h]	2
After 4 weeks storage at 23°C / 50% rh       Tensile strength     ISO 37     [N/mm <sup>2</sup> ]     2,10       Elongation at break     ISO 37     [%]     200       Modulus at 100% elongation     ISO 37     [N/mm <sup>2</sup> ]     1,80       Hardness Shore A     ISO 868     55       Volume loss     [%]     <-2	Skin forming time at 23°C / 45 % r.h.		[min]	30
Elongation at break     ISO 37     [%]     200       Modulus at 100% elongation     ISO 37     [N/mm²]     1,80       Hardness Shore A     ISO 868     55       Volume loss     [%]     < -2	• • •			
Modulus at 100% elongation     ISO 37     [N/mm <sup>2</sup> ]     1,80       Hardness Shore A     ISO 868     55       Volume loss     [%]     < -2	Tensile strength	ISO 37	[N/mm <sup>2</sup> ]	2,10
Hardness Shore A ISO 868 55   Volume loss [%] <-2	Elongation at break	ISO 37	[%]	200
Volume loss [%] < -2	Modulus at 100% elongation	ISO 37	[N/mm <sup>2</sup> ]	1,80
	Hardness Shore A	ISO 868		55
	Volume loss		[%]	< -2
	Temperature resistance		[°C]	-40 / +100

These figures are only intended as a guide and should not be used in preparing specifications.

The data presented in this medium are in accordance with the present state of our knowledge but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this medium should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also being used. The information provided by us does not absolve the user from the obligation of investigating the possibility of infringement of third parties' rights and, if necessary, clarifying the position. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the product for a particular purpose.

The management system has been certified according to DIN EN ISO 9001 and DIN EN ISO 14001

For technical, quality, or product safety questions, please contact: MASTICI VOTTERO s.n.c. 10040 La Cassa (TO) - via Torino 44 info@masticivottero.com www.masticivottero.com